



**TAPADIA  
POLYESTERS**


# TAPADIA POLYESTERS PVT LTD

D4, Butibori MIDC, Butibori - 441122 Maharashtra, India  
Mobile: +91 9823652225  
salestapadia@gmail.com | [www.tapadiapolyesters.com](http://www.tapadiapolyesters.com)

## PRODUCT DATA SHEET

## T-PET HPCM-4

### Film Structure



### Product Description:

Hi-Bond MET PET Film for Pasteurization Application (Metalized on coated side/ other side corona)

Tapadia®T-MET PET is a normal density biaxially oriented Metalized polyester film made of polyethylene terephthalate (PET). Metalized on pre-coated chemical surface and other side corona. Metallization on chemical coated surface offers high metal adhesion performance.

Property		Unit	Test Method	Typical Value
Thickness		Micron	Internal	10,12
Yield		m2/kg	Internal	59.5
Tensile Strength	MD	Kg/cm2	ASTM D 882	2000
	TD			1900
Elongation	MD	%	ASTM D 882	90
	TD			90
Heat Shrinkage 150°C 30 min	MD	%	ASTM D 1204	2.8
	TD			0.4
Co-Efficient of Friction	Static	---	ASTM D 1894	0.55
	Dynamic			0.50
WVTR (38 °C & 90%RH) (Max)		gm/m2/day	ASTM F 1249	1.0
OTR (23 °C & 0%RH) (Max)		cc/m2/day	ASTM D 3985	1.0
Optical Density (±5%)		---	Optel Make Instrument	2.2
Metal Bond Strength (Min)		Gm/25mm	AIMCAL TP 105-92	800

MD= MACHINE DIRECTION \*TD= TRANSVERSE DIRECTION

**\*The data above only represents 12 Micron, specific data for other microns will be provided on request.\***

### STORAGE & HANDLING

T-PET does not require special storage conditions. It is recommended to storage below 30°C in order to avoid any deterioration of the film surface properties. It is advisable to use the material on FIFO basis. The film should be kept at operating environment for 24 hours before processing. T-PET is best suitable for use up to 3 months from date of dispatch.

### FOOD CONTACT

T-PET complies with EC and FDA regulations. Specific document and MSDS are available on request.

### DISCLAIMER

It is the responsibility of our customer to determine that their use of our product(s) is safe, lawful, and technically suitable in their intended applications. The Values given in the technical data sheet represent typical values based on the best of our knowledge as on date when the data was compiled. It is offered solely to provide possible suggestions for your own experimentation and not as a guarantee for the material supplied. The user is solely responsible for the end use of the product and needs to perform their own tests to confirm the product suitability I compatibility in all respects. TPPL gives no warranty or accept liability for any loss and fitness of the product for any specific purpose. TPPL serves the right to change the technical data sheet at any time for enhancing the quality of the products without prior information.

**\*\*TDS issued on 08<sup>th</sup> July 2025 . All Previous versions for this grade are invalid.**